




凯美亚化学有限公司
KEMIACHEM CO., LIMITED.

Technical Data Sheet

| | | | | | | | | | | |
|------------------|---|-------|-------|-------|-------|--|-------|-------|--------|--------|
| Product Name | Flourspar | | | | | | | | | |
| Model Number | CAF2 65 70 75 80 85 90 93 95 97 | | | | | | | | | |
| Shape | Lumps | | | | | | | | | |
| Specification | CaF2 | 65% | 70% | 75% | 80% | 85% | 90% | 93% | 95% | 97% |
| | SiO2 | ≤33 | ≤28 | ≤23 | ≤15.0 | ≤9.0 | ≤5.0 | ≤1.5 | ≤1.5 | ≤1.5 |
| | CaO3 | ≤3.0 | ≤3.0 | ≤3.0 | ≤3.0 | ≤3.0 | ≤3.0 | ≤1.5 | ≤1.5 | ≤1.3 |
| | S | ≤0.1 | ≤0.1 | ≤0.1 | ≤0.1 | ≤0.1 | ≤0.1 | ≤0.09 | ≤0.05 | ≤0.03 |
| | P | ≤0.1 | ≤0.1 | ≤0.1 | ≤0.1 | ≤0.1 | ≤0.1 | ≤0.09 | ≤0.05 | ≤0.03 |
| | H2O | ≤1.5 | ≤1.5 | ≤1.5 | ≤1.5 | ≤1.5 | ≤1.5 | ≤1.3 | ≤1.0 | ≤0.5 |
| | Fe2O3 | ≤0.04 | ≤0.04 | ≤0.04 | ≤0.02 | ≤0.02 | ≤0.02 | ≤0.01 | ≤0.001 | ≤0.001 |
| Application | <p>Fluorspar is used to make glazes and surface treatments that produce hard glossy surfaces, opalescent surfaces and a number of other appearances that make consumer glass objects more attractive or more durable.</p> <p>Mineralized cement clinker agent, can reduce the sintering temperature, easy to calcination, sintering time and save energy.</p> <p>Chemical industry to manufacture hydrofluoric acid (HF). The HF is then used to manufacture a variety of products which include: fluorocarbon chemicals, foam blowing agents, refrigerants and a variety of fluoride chemicals</p> | | | | | | | | | |
| Size | 1-10mm 1-25mm 35-40mm | | | | | | | | | |
| Packing | In 1 MT bulk big bag or according the buyer requirement | | | | | | | | | |
| Delivery detail | Within 20 days after the receipt of L/C or advance payment | | | | |  | | | | |
| Quantity /20'FCL | 23-25 MTS | | | | | | | | | |