

Technical Data Sheet

Product Name	Silicon Manganese
Model Number	65/17 60/14
Shape	Lumps
Specification	65/17 Grad Mn:65%min Si:17%max C:1.5%max P:0.3%max S:0.04%max 60/14 Grad Mn:60%min Si:14%max C:2.5%max P:0.3%max S:0.04%max
Application	Silicon manganese can be used as a compound deoxidant,desulphurizer and alloying addition in steel making, and can also be used as areductant in medium-low carbon manganese iron production or in metal manganese production by electricsilicon heating. Special requirements on chemical compositions and physical properties of the alloy from the customers can be discussed and defined by both sides.
Size	10-50mm 10-100mm 50-100mm
Packing	In 1 MT bulk big bag or according the buyer requirement
Delivery detail	Within 20 days after the receipt of L/C or advance payment
Quantity /20'FCL	23-25 MTS